

Belzona 4151

FN10006 (MAGMA-QUARTZ RESIN)



INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

Any surfaces to which **Belzona® 4151** is to be applied must be clean, firm and dry. Old concrete should be washed down with detergent to remove oil, grease and dirt. Clean water should then be used to wash away the detergent. All paint, tar and any other coatings must be removed.

New concrete should be allowed to cure for a minimum of 28 days or until the moisture content is below 6% using a Protimeter.

Horizontal concrete surfaces and new concrete will show the phenomenon of surface laitence and this must be removed by mechanical scarification. Vertical surfaces should be wire brushed to remove loose surface material.

Belzona® 4111 (Magma-Quartz) and **Belzona® 4131** (Magma-Screed) must be overcoated within 6 hours. If allowed to cure for longer than this time, the surface must be thoroughly abraded and any contamination removed with a suitable cleaner. In all instances any loose dust produced by surface preparation techniques should be vacuumed clear.

2. COMBINING THE REACTIVE COMPONENTS

Empty the entire contents of the Base and Solidifier units into a suitable mixing vessel. Mix thoroughly for 3 minutes until a homogeneous mix is achieved then immediately proceed to Stage 3, "Application".

NOTES:

1. WARNING

UNDER NO CIRCUMSTANCES SHOULD COMPLETE UNITS BE MIXED AND LEFT TO STAND, AS THE LARGE EXOTHERM PRODUCED WILL GREATLY REDUCE THE USABLE LIFE OF THE MIXED MATERIAL.

IF DIFFICULTY IS ANTICIPATED IN APPLYING ALL OF THE MATERIAL WITHIN ITS WORKING LIFE, IT SHOULD BE SPLIT BETWEEN TWO OR MORE OPERATIVES TO APPLY.

ALTERNATIVELY, SMALLER QUANTITIES SHOULD BE MIXED (see 2 below).

2. MIXING SMALL QUANTITIES

For mixing small quantities of **Belzona® 4151** use:
2 parts Base to 1 part Solidifier by volume or
2.3 parts Base to 1 part Solidifier by weight.

Mix thoroughly for 2 minutes to achieve a homogeneous mix, then proceed to Stage 3 "Application".

3. WORKING LIFE

From the commencement of mixing, **Belzona® 4151** must be applied within the times shown below:

Temperature	Use all material within
41°F/ 5°C	45 min
50°F/10°C	32 min
59°F/15°C	25 min
68°F/20°C	16 min
77°F/25°C	12 min

4. VOLUME CAPACITY OF MIXED BELZONA® 4151
272 cu.in. (4455 cc) per 4.95 kg.

3. APPLYING BELZONA® 4151

FOR BEST RESULTS

Do not apply when:-

- (i) The temperature is below 41°F (5°C) or the relative humidity is above 90%.
- (ii) Rain, snow, fog or mist is present.
- (iii) There is moisture on the surface or is likely to be deposited by subsequent condensation.
- (iv) The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

- a) Apply **Belzona® 4151** with a good quality brush, to give a practical coverage rate of 167 sq.ft. (15.5 m²) per 4.95 kg unit. See Note 2 below regarding application to vertical surfaces.
- b) Where a second coat is required, this should be applied as soon as it is possible to do so without disturbing the first coat, and never after longer than 2 hours.

Should this overcoating interval be exceeded, the first coat should be allowed to harden, and abraded prior to applying the second coat. (Alternatively, see Note 3 below for large applications).

- c) The second coat of **Belzona® 4151** should be applied directly after mixing.

NOTES:

1. Film thickness and coverage rate will vary with porosity and profile of the substrate.
2. To avoid sagging on vertical surfaces, film thickness should not exceed 5 mil (125 microns).
3. On larger applications where it is not possible to overcoat **Belzona® 4151** within the maximum overcoating time, **Belzona® 4911** (Magma TX Conditioner) should be adopted instead of the first coat of **Belzona® 4151**. This material should be applied at a practical coverage rate of 79.0 sq.ft. (7.33 sq.m.) per 3 kg unit irrespective of whether on a horizontal or vertical surface. The **Belzona® 4151** should be applied as soon as possible to do so without disturbing the **Belzona® 4911**, and never in excess of the 6 hour maximum overcoating time.

4. CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. Methyl ethyl ketone (MEK). Application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

4. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 4151** to solidify as below before subjecting it to the conditions indicated:

	To resist pedestrian traffic	Full mechanical hardness	Full chemical resistance
41°F/ 5°C	16 hours	2 days	14 days
59°F/15°C	6 hours	24 hours	10 days
77°F/25°C	4 hours	16 hours	5 days

BELZONA® 4151 MUST NOT BE EXPOSED TO MOISTURE UNTIL FULL CURE HAS BEEN ACHIEVED OTHERWISE SURFACE WHITENING WILL OCCUR.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2019 Belzona International Limited. Belzona® is a registered trademark.

Belzona products are manufactured under an ISO 9001 Registered Quality Management System

